

Build fast to last

3M™ VHB™ Tapes...proven worldwide for greater productivity, design flex



For more than 20 years, engineers worldwide have been specifying 3M[™]VHB[™]Tapes to permanently bond and seal many surfaces for all the reasons shown here. And in commercial construction from Australia to Brazil, the United States to

Switzerland, applications for these double-sided acrylic foam tapes have continued to expand indoors and outdoors for panel to frame bonding and stiffener attachment.

exibility, and reliability



Expands the range of design and material options

- Join many surfaces including dissimilar materials; tape prevents bi-metallic corrosion
- · Use lighter weight and thinner substrates
- Bond most painted and powder coated surfaces, and hard-to-bond plastics such as acrylic and polycarbonate




• Canopies systems

• Decorative metal trim


• And more...

Around the building and around the world...a




Sao Paulo, Brazil Architect: Carlos Bratke, 1995 Aluminum stiffeners bonded to ACM panels.









adhesive technology for the art and productivity of commercial construction











High holding power and long term reliability of




Dearborn Center, Chicago, IL, USA Fabricator: Copper Sales Una-Clad, 2003 Stiffeners bonded to exterior metal trim cladding.








y outdoors and indoors

Burj Al Arab Hotel, Dubai, UAE Architect: W.S. Atkins and Partners, 1999 Aluminum composite panels bonded to framework to resist high wind loads.










Tamedia Building, Zurich, Switzerland Facade design: Soder AG, 2001 Glass steps bonded to varnished steel frame.



Jumeirah Beach Hotel, Dubai, UAE Curtain wall design: Schmidlin AG, 1998 Aluminum panels bonded to steel stiffeners.




to permanently bond many materials flat or curved









Samsung Medical Center, Seoul, South Korea Architect: Samoo Architects and Engineers, 1995 Aluminum stiffeners bonded to aluminum panels.

Technical information

A. Structural Performance Tests

Architectural metal panels assembled using 3M[™]VHB[™]Tapes were given structural performance tests at Construction Research Laboratory (Miami, FL). Each panel measured 5 ft x 8 ft (1524 mm x 2438 mm) and was built with a perimeter frame and three stiffeners attached to the aluminum or ACM sheet using only VHB tape. The tests were performed according to ASTM E330 "Standard Test Method for Structural Performance of Exterior Windows, Curtain Walls, and Doors by Uniform Static Air Pressure Difference". The panels survived pressures up to 120 psf (5.7 kPa) in both directions, which corresponds to a sustained wind speed of 220 mph (355 kph). The VHB tapes demonstrated excellent performance, even after the panels and stiffeners themselves had shown permanent deformation in these simulated high winds.

A duplicate set of panels constructed using VHB tapes was subjected to non-ambient temperature structural performance tests. The panels were subjected to positive and negative pressures up to 60 psf (2.9 kPa) at cold (-20°F, -29°C), ambient (90°F, 32°C), and hot (150°F, 66°C) outside air test temperatures, which were the most extreme temperatures obtainable in this specific test configuration. Subsequent inspection showed VHB tapes withstood these wind pressures at the temperature extremes, and provided excellent performance despite the panels and stiffeners exerting high stresses on the tapes at all three test temperatures.

Aluminum panels of another design were bonded with VHB tape and tested in accordance with AS 2047 "Windows in Buildings" by the CSIRO Division of Building, Construction and Engineering (Australia). The panels were subjected to differential pressures up to 146 psf (7.0 kPa) with no signs of failure. This pressure represents a wind speed of approximately 242 mph (390 kph).

B. Hurricane Impact and Pressure Cycling Tests

Architectural metal panels assembled with VHB tapes were subjected to impact and pressure cycling tests to determine their ability to survive a hurricane or other high wind event. This testing was also performed at Construction Research Laboratory (Miami, FL). The impact test was performed in accordance with ASTM

E1996 "Standard Specification for Performance of Exterior Windows, Curtain Walls, Doors and Storm Shutters Impacted by Windborne Debris in Hurricanes", using the most severe wind zone classification for non-essential buildings. The impacts resulted in heavy damage to the panels, frame, and stiffeners, but the VHB tapes held fast and even expanded to maintain contact with both dented surfaces.

The same panels were then given the pressure cycling sequence specified by Dade County Specification PA-203 using the test method provided in ASTM E1886 "Standard Test Method for Performance of Exterior Windows, Curtain Walls, Doors, and Storm Shutters Impacted by Missiles and Exposed to Cyclic Pressure Differentials". This resulted in a total of 1,342 pressure cycles (in the positive and negative wind directions) on the panels using a building design pressure of 40 psf (1.9 kPa). Visual inspection after the test indicated the VHB tapes had maintained full contact to all stiffeners with no loss of adhesion. The pressure cycling sequence was then repeated using a building design pressure of 60 psf (2.9 kPa) for an additional 1,342 cycles. Two VHB tapes maintained complete adhesive contact with the stiffeners after this additional pressure cycling, indicating excellent performance throughout the hurricane-related tests.

C. Fire Tests

Several VHB tapes were bonded between pieces of aluminum (similar to architectural metal panel applications) and tested by the Warrington Research Centre (United Kingdom) for fire performance according to British Standard 476 Part 6 "Method of Test for Fire Propagation for Products" and Part 7 "Surface Spread of Flame Test for Materials". No surface spread of flame occurred, and the products complied with the requirements for a Class 0 surface.

A different VHB tape bonded in a similar construction was tested to AS 1530 III "Early Fire Hazard Properties of Materials" by the CSR Concord Research & Development Centre (Australia). This testing yielded the following fire rating indices:

 $\begin{array}{lll} & & & & & & \\ & & & & \\ & & & \\ & & & \\ & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ & & \\ &$

D. Weathering Resistance

Bonds made with VHB tapes have been exposed on outdoor weathering decks in Arizona, Florida, Minnesota, and Japan to collect data on the long-term weathering resistance of VHB tapes. These tests typically showed full bond strength retention after 5 years of exposure in these real-life weather tests, at which point the tests were discontinued.

Numerous accelerated aging tests have also been performed which subject a bond made with VHB tape to heat, humidity, and concentrated UV light exposure to simulate outdoor weather conditions. For example, tests have demonstrated that VHB tape bond strength, as performed in a dynamic overlap shear test, typically maintains its original performance even after 7000 hours of exposure to these harsh conditions, at which point the tests were discontinued.

E. Solvent Resistance

Test results show no effect on VHB tape bond performance after splashes or incidental contact with a wide variety of solvents (such as fuels, alcohols, adhesive removers, weak acids, and weak bases).

F. Compatibility with Silicone Sealants

VHB tapes have been tested for compatibility with several different silicone sealants using the procedure described in ASTM C1087 "Standard Test Method for Determining Compatibility of Liquid-Applied Sealants with Accessories Used in Structural Glazing Systems". The results showed VHB tapes to be compatible with silicone sealants, with no noticeable color change and no loss of adhesion to glass substrates.

G. Sealing

3M[™]VHB[™]Tapes can provide an excellent seal against moisture. They also form an excellent barrier to prevent galvanic corrosion between dissimilar metals.

Architectural metal panels with a perimeter frame attached only with VHB tapes were subjected to water leakage tests in accordance with ASTM E331 "Standard Test Method for Water Penetration of Exterior Windows, Skylights, Doors, and Curtain Walls by Uniform Static Air Pressure Difference" at Construction Research Laboratory (Miami, FL). The results indicated that, with proper tape application and perhaps a small amount of silicone sealant over the tape seams, that VHB tape can provide an excellent seal against water penetration.

H. Design Considerations

Adhesion - VHB tapes are ideal for bonding to a variety of substrates, including most metals, glass, plastics, composites, and painted surfaces. Each product in the VHB tape family has specific features, including the ability to bond to different types of materials. Determination of whether a specific VHB tape is fit for a particular application should include adhesion testing with the actual substrates.

Static Loads - For static tensile or shear loads (such as dead weight loads, snow loads and other long-term loads), a design strength of 0.25 psi (1.7 kPa) can generally be used. This means that 4 sq in of VHB tape per 1 lb (55 sq cm per 1 kg) should be used to support static loads. This guideline provides a safety factor of at least 5.

Dynamic Loads - For dynamic tensile or shear loads (such as wind loads), a design strength of 12 psi (85 kPa) can generally be used for most VHB tapes, while a design strength of 9 psi (60 kPa) should be used for the VHB tape 5952 series. These guidelines provide a safety factor of at least 5. These values can easily be adjusted to incorporate a different safety factor. For example, a safety factor of 3 would result in a design strength of 20 psi (140 kPa) for most VHB tapes, and 15 psi (105 kPa) for the VHB tape 5952 series.

Differential Movement - VHB tapes typically perform well in applications where the two bonded surfaces experience movement relative to each other, such as with thermal expansion and contraction. Most VHB tapes can tolerate shear movement up to 3 times their original thickness (300% shear strain). Since bonds made

with VHB tapes will be more flexible than other joining methods, suitable design modifications may be needed to achieve required stiffness.

Tape Thickness - The optimal thickness of VHB tape for a particular application depends on the size, rigidity, and flatness of the substrates, as well as the amount of application pressure applied to mate the surfaces together. In general, thicker tapes will handle greater mismatch and differential thermal movement between surfaces, and provide better contact and sealing.

Example - A panel designer has tested adhesion to the actual job materials and determined a suitable VHB tape for a perimeter frame attachment application. The panels measure 5 ft x 10 ft (1524 mm x 3048 mm), are made of 1/8" (3 mm) thick aluminum sheet, and weigh 88 lb (40 kg). The designer uses the 0.25 psi (1.7 kPa) static design strength to calculate that 1" (25 mm) wide VHB tape will meet the static load requirement. The designer then uses the 12 psi (85 kPa) dynamic design strength and a trapezoidal distribution of wind forces to calculate that 1" (25 mm) wide VHB tape will also meet the dynamic load requirement for the building, which has a design wind pressure of 58 psf (2.8 kPa). Finally, the designer calculates the amount of movement and mismatch possible between the panel and frame, and determines this will result in less than 300% shear strain on the VHB tape.

I. Important Note

The details about each architectural metal panel application (such as panel design, materials, surface preparation, selected VHB tape, and building-specific requirements) can affect the

use and performance of a VHB tape. Therefore, VHB tapes should be thoroughly evaluated by the user under actual use conditions with intended substrates to determine whether a specific VHB tape is fit for a particular purpose and suitable for user's method of application, especially if expected use involves extreme environmental conditions.

J. Warranty

VHB tapes can provide the strength and durability needed in the assembly of architectural metal panels. For qualifying applications, 3M will also provide an application warranty to provide you and your customers with even more confidence that VHB tapes can deliver high performance and long-term reliability. Once your application and assembly processes are approved, 3M guarantees that VHB tape will not fail for the warranty period. See your 3M representative for details on obtaining the warranty.

K. Other References

The above technical background provides only a brief summary about the performance of VHB tapes in construction applications. For complete details and more technical information, please refer to the following documents:

- refer to the following documents:

 1. Technical data page: "VHB Tapes for Construction Applications"
- Technical bulletin: "Structural Performance Tests of VHB Tapes in Architectural Metal Panels"
- 3. Technical bulletin: "Surface Preparation for 3M VHB Tape Applications"
- 4. Technical bulletin: "3M VHB Tape Durability"

3M[™]VHB[™] Tapes for Architectural Metal Panels

Product Number	Tape Thick- ness w/o	Description	Adhesive Type	Temper	ature	Solvent Resist-			Application Ideas
	Liner Mils			Short	Long	ance	HSE	LSE	
4941 4941F 4956 4956F 4991	45 mil (1.1 mm) 45 mil (1.1 mm) 62 mil (1.55 mm) 62 mil (1.55 mm) 90 mil (2.3 mm)	Dark gray, closed-cell acrylic foam carrier. Conformable. Good adhesion to many painted metals. Plasticizer resistant.	Acrylic	250°F (121°C)	200°F (93°C)	High	High	Med	Attach stiffeners and trim to metal sheet or painted ACM panels. Bond and seal perimeter frame to metal sheet or ACM panels.
4950 4955 4959	45 mil (1.1 mm) 80 mil (2.0 mm) 120 mil (3.0 mm)	White, closed-cell acrylic foam carrier. General purpose adhesive.	Acrylic	300°F (149°C)	200°F (93°C)	High	High	Low	Attach stiffeners and trim to bare metal panels. Bond and seal perimeter frame to bare metal panels.
5952 5962	45 mil (1.1 mm) 62 mil (1.55 mm)	Black, closed-cell acrylic foam carrier. Conformable. Good adhesion to many painted surfaces, including powder coatings.	Synthetic	300°F (149°C)		High	High	Med	Attach stiffeners and trim to painted ACM panels. Bond and seal perimeter frame to painted ACM panels.

Relative Adhesion: HSE – High Surface Energy LSE – Low Surface Energy

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Architectural Panel Stiffener Cost Comparison

	Silicone Sealant	Stud Bolts	3M™ VHB™ Tape
Attachment Time	5 minutes (clean surfaces, apply spacer tape, apply silicone sealant, clean-up)	7 minutes (drill holes, mark stud locations, weld studs, fasten washers and nuts)	3 minutes (clean surfaces, apply tape, remove liner, place stiffener, roll down)
Labor Cost	\$4.15	\$5.85	\$2.50
Materials	spacer tape, structural silicone sealant	stud bolts, washers, nuts	tape \$1.50
Material Cost	\$2.30	\$0.60	
Total Cost	\$6.45	\$6.45	\$4.00
Savings per Stiffener			\$2.45

Figures are estimates based on the attachment of a 4 foot long 1.5 inch wide stiffener onto the back side of an architectural panel. Labor costs use a \$25 per hour burden rate and include two employees.

Finishing, masking, and protecting metal surfaces

Beyond bonding with 3M[™] VHB[™] Tape, 3M industrial technologies can help you finish, mask, and protect the surfaces of architectural metal panels.



3M Abrasive Systems: From a wide selection of 3M non-woven abrasive products you can find wheels and discs to quickly deburr, blend and finish any metal. Special construction runs cool and long for cost-effectiveness.



3M Masking Tapes: With this extensive line you have choices in holding power, paint edge sharpness, temperature resistance, and clean removal to meet the productivity and quality requirements of any painting method.



3M Protective Films: To protect metal surfaces during processing, shipping and installation, these polyethylene films offer combinations of adhesive sticking power and removability for the demands of various conditions

For Additional Information: To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550. Address correspondence to 3M Industrial Adhesives and Tapes Division, 3M Center, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144, Our fax number is 651-778-4244.

Limited Product Warranty: 3M warrants for 24 months from the date of manufacture, that 3M™VHB™Tape will be free of defects in material and manufacture. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. This warranty does not cover damage resulting from the use or inability to use 3M VHB Tape due to misuse, workmanship in application, or application or storage not in accordance with 3M recommended procedures. Important Notice: User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of these materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application. Limitation of Remedies and Liability: If the 3M™VHB™ Tape is proved to be defective within the warranty period stated above, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M™VHB™TAPE. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.



Industrial Business **Industrial Adhesives and Tapes Division**

3M Center Bldg. 21-1W-10 900 Bush Ave. St. Paul, MN 55144 www.3M.com/vhb



Recycled paper 40% pre-consumer 10% post-consumer Printed in U.S.A. Blar 4080373 Copyright © 2004 3M 70-0709-3965-0